

SPECIFICATION SHEET

1200N NON-WOVEN GEOTEXTILE

1200N is manufactured using polypropylene fibers that are formed into a dimensionally stable network, which allows the fibers to maintain their relative position. 1200N resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

| PROPERTY | TEST METHOD | MARV ENGLISH | MARV METRIC |
|---------------------------|-------------|------------------------|--------------------------|
| Tensile Strength (Grab) | ASTM D4632 | 300 x 300 lbs | 1,356.7 x 1,356.7 N |
| Elongation (Grab) | ASTM D4632 | 50% x 50% | 50% x 50% |
| Trapezoidal Tear Strength | ASTM D4533 | 115 x 115 lbs | 511 x 511 N |
| CBR Puncture | ASTM D6241 | 825 lbs | 3,670 N |
| UV Resistance (500 hrs) | ASTM D4355 | 70% | 70% |
| Apparent Opening Size* | ASTM D4751 | 100 US Std. Sieve | 0.150 mm |
| Permittivity | ASTM D4491 | 1.0 sec ⁻¹ | 1.0 sec ⁻¹ |
| Water Flow Rate | ASTM D4491 | 75 gpm/ft ² | 3,055 lpm/m ² |

*Maximum Average Roll Value

| PROPERTY | TEST METHOD | TYPICAL ENGLISH | TYPICAL METRIC |
|-----------------|-------------|---------------------|--------------------|
| Roll Dimensions | Measured | 15 ft x 300 ft | 4.6 x 91.4 m |
| Roll Area | Measured | 500 yd ² | 418 m ² |

The information provided is for reference purposes only and is not intended as a warranty or guarantee whether implied or inferred. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The property values listed above are subject to change without notice. BW Geotextiles assumes no liability in connection with the use of this information and product.

1239 Notre Dame Drive, Box 178
 Petersburg, ON N0B 2H0
 Phone: (519)778-1953 Toll Free: 1-844-778-1953
www.bwgeotextiles.com

09/29/2023