

SPECIFICATION SHEET

200W WOVEN GEOTEXTILE

200W is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. 200W resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV ENGLISH	MARV METRIC
Tensile Strength (Grab)	ASTM D4632	200 x 200 lbs	890 x 890 N
Elongation (Grab)	ASTM D4632	15% x 15%	15% x 15%
Trapezoidal Tear Strength	ASTM D4533	75 x 75 lbs	330 x 330 N
CBR Puncture	ASTM D6241	700 lbs	3,113 N
UV Resistance (500 hrs)	ASTM D4355	70%	70%
Apparent Opening Size*	ASTM D4751	40 US Std. Sieve	0.425 mm
Permittivity	ASTM D4491	.05 sec ⁻¹	.05 sec ⁻¹
Water Flow Rate	ASTM D4491	5 gpm/ft ²	204 lpm/m ²

*Maximum Average Roll Value

PROPERTY	TEST METHOD	TYPICAL ENGLISH	TYPICAL METRIC
Roll Dimensions	Measured	12.5 ft x 432 ft 15 ft x 360 ft	3.8 x 131.7 m 4.6 x 110 m
Roll Area	Measured	600 yd ²	502 m ²

The information provided is for reference purposes only and is not intended as a warranty or guarantee whether implied or inferred. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The property values listed above are subject to change without notice. BW Geotextiles assumes no liability in connection with the use of this information and product.

1239 Notre Dame Drive, Box 178
Petersburg, ON N0B 2H0
Phone: (519)778-1953 Toll Free: 1-844-778-1953
www.bwgeotextiles.com

10/03/2023