

# SPECIFICATION SHEET

## 400N NON-WOVEN GEOTEXTILE

400N needle-punched nonwoven geotextile is manufactured using polypropylene fibers that are formed into a dimensionally stable network, which allows the fibers to maintain their relative position. 400N needle-punched nonwoven geotextile resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV ENGLISH	MARV METRIC
Tensile Strength (Grab)	ASTM D4632	100 x 100 lbs	445 x 445 N
Elongation (Grab)	ASTM D4632	50% x 50%	50% x 50%
Trapezoidal Tear Strength	ASTM D4533	45 x 45 lbs	200 x 200 N
CBR Puncture	ASTM D6241	300 lbs	1,334
UV Resistance (500 hrs)	ASTM D4355	70%	70%
Apparent Opening Size*	ASTM D4751	70 US Std. Sieve	0.212 mm
Filtration Opening Size	CAN/CGSB-148.1 N°10-94		0.108mm
Permittivity	ASTM D4491	2.0 sec <sup>-1</sup>	2.0 sec <sup>-1</sup>
Water Flow Rate	ASTM D4491	140 gpm/ft <sup>2</sup>	5,704 lpm/m <sup>2</sup>

\*Maximum Average Roll Value

- Filtration Opening Size (FOS) tested by CTT Group.

PROPERTY	TEST METHOD	TYPICAL ENGLISH	TYPICAL METRIC
Roll Dimensions	Measured	12.5 ft x 360 ft	3.8 x 110 m
		15 ft x 360 ft	4.6 x 110 m
Roll Area	Measured	500 yd <sup>2</sup>	418 m <sup>2</sup>
		600 yd <sup>2</sup>	502 m <sup>2</sup>

The information provided is for reference purposes only and is not intended as a warranty or guarantee whether implied or inferred. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The property values listed above are subject to change without notice. BW Geotextiles assumes no liability in connection with the use of this information and product.